

Naturally.



Corr/12-2

Product Data Sheet

Binol Corr E10

Binol Corr E10 is a water miscible fluid used for temporary corrosion protection of metal components indoors up to 12 months. The product may be applied by dipping or by spraying.

Recommended concentrations: 3-6%

Physical and Chemical Data (typical)

Analysis	Method	Unit	Results
Concentrate			
Viscosity at 40°C	ISO 3104	mm ² /s	2
Density at 20°C	ISO 3675	kg/m ³	App. 1060
pH	DIN 51 369		App. 9,8
Flash Point	SIS 15 02 02	°C	>200
Boiling Point	Own	°C	approx. 100
Freezing Point	Own	°C	0
Colour	Optical		Water white/ yellow
Smell	Nasal		Faint
Diluted (5%)			
Appearance	Optical		transparent
pH	DIN 51 369		9,7

Handling

- Storage
- Packaging

Handling and storage between +5 to +40°C
200 l drum.

A company in the AAK Group

Binol AB
SE-374 82 KARLSHAMN
SWEDEN

Phone +46 454 828 00
Fax +46 454 752070

binol@aaak.com
www.binol.com

556111-3472
SE556111347201
Registered office: Karlshamn

